

U-POL[®]

HIGH VISCOSITY DOLPHIN GLAZE POLYESTER PUTTY

Description

DOLPHIN GLAZE HV is a two component chemical liquid used for the final skimming of a polyester putty repair or for direct application onto minor imperfections on bodywork prior to over painting. **DOLPHIN GLAZE HV** is designed for the professional user and combines good levelling properties together with easy sanding.

Health and Safety Statement

FOR PROFESSIONAL USE ONLY. Read full instructions before use. **IMPORTANT:** This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.

Surface preparation and instructions for use

DOLPHIN GLAZE HV polyester putty can be used on the following surfaces:-

- Bare steel - degrease and abrade with P120 abrasive.
- Galvanised and other Zinc coated steels - degrease and abrade with P120 abrasive.
- Aluminium – degrease and sand with P120 abrasive.
Do not apply over etch primer.
- Original paint surfaces - degrease and abrade with P180 – 320 abrasive.

Mixing ratio

100 parts by weight **DOLPHIN GLAZE HV** polyester filler, 2 parts by weight **U-POL** hardener for polyester fillers.

The exact mixing ratio is not critical, although over or under catalyzation may affect the gel time.

DOLPHIN GLAZE HV is a thick liquid and should be mixed in small quantities on a flat non-porous surface. To obtain optimum results apply the mixed liquid in small quantities to form a thin film - during cure surface imperfections will flow out to leave a level repair which requires only a small amount of sanding.

Pot life

Once mixed, 4 -5 mins. at 68°F with 2% hardener.

Tools

Mixing board, filler knife, plastic or rubber spreader.

Drying time

Sandable after 30 mins. at 68°F.

Over-painting

DOLPHIN GLAZE HV polyester putty can be over-painted with most paint systems.

Product codes

UP 0740 - 440ml plastic bag.

U-POL US, Inc., 630 Selvaggio Dr, Suite 300, Nazareth, PA 18064
Tel: (800) 340 7824; Fax: (800) 787 5150
Email: sales-us@u-pol.com Website: www.u-pol.com