



## BULLDOG® VOC Compliant Adhesion Promoter

---

GTPO125, QTPO125 (Gallon, Quart Liquid)



**BULLDOG® VOC Compliant Adhesion Promoter** is designed to meet all California regulations and has the same features and benefits of our current BULLDOG® Adhesion Promoter. It is a patent-pending, one-component formula that promotes adhesion on all types of automotive plastic.

- Compliant with California SCAQMD Rule 1151 – Adhesion Promoter, effective 1/1/2010.
- Provides superior adhesion
- No waste – unused product can be poured back into the can
- One component formula
- Adds flexibility
- Fills 320 grit scratches

---

### Compatible Coatings:

- All solvent-based urethane, epoxy, or acrylic lacquers, primers, sealers and basecoats.
- TPO125 is compatible with waterborne basecoat systems, as long as the primer is applied according to manufacturer's instructions.

### Related Products:

PABC124 – BULLDOG® Abrasive Cleaner

**Note:** ETPO123B BULLDOG® Adhesion Promoter 15oz Aerosol is **not** affected by Rule 1151, and can be sold and used in the state of California. BULLDOG® Adhesion Promoter (QTPO123, GTPO123) will continue to be available in all areas of the country not subject to VOC restrictions.





## **BULLDOG® VOC Compliant Adhesion Promoter**

---

### **DIRECTIONS FOR USE:**

(Read all cautions and directions on the product label prior to use.)

#### **Adhesion Promoter for Plastic Parts:**

1. Clean all areas to be painted with BULLDOG® Abrasive Cleaner, using a gray scuff pad.
  2. Rinse thoroughly with plenty of water. Wipe dry using a clean cloth and an air hose.
  3. Sprinkle an area with water. If water sheets, you are ready to proceed with BULLDOG® application. If water beads, the cleaning steps 1-3 must be repeated.
  4. Blow and tack surface.
  5. Using a spray gun, apply an even, light coat. Wait 25 to 30 minutes before applying the next coating. *Dry times may vary based on temperature and humidity.*
  6. Apply basecoat and clearcoat according to manufacturer's instructions.
- 

**Cleanup:** All tools and spills should be cleaned immediately with Naked Gun® VOC Compliant Spray Gun Cleaner (CGC112). Clean spray gun according to manufacturer's instructions.

#### **Notes:**

- BULLDOG® has a 24 hour open time. If the part is left longer than 24 hours, tack, and apply 1 even, light coat of BULLDOG® before applying basecoat or primer.
  - Tint up to 30% with desired urethane or acrylic lacquer basecoat or toner for better hide. BULLDOG® may *not* be added to waterbased toners or basecoats.
  - This product may not be compatible with all surfaces and all conditions surrounding application. Before applying to any surface, always test in an inconspicuous area to ensure no damage will result.
  - Recommended HVLP Spray Gun Tip Size: 1.3mm – 1.4mm
  - If thinning is necessary, BULLDOG® can be reduced up to 10% with KLEAN-STRIP® Acetone.
- 





## BULLDOG® VOC Compliant Adhesion Promoter

|  | GTP0125/QTPO125  |
|--|--|
| <b>Appearance</b>                        | Liquid, mobile, hazy, light yellow to purple               |
| <b>Vapor Density</b>                     | Heavier Than Air   |
| <b>Percent Volatile</b>                  | Total Volatiles: 80.4% Water: 0% VOC Exempt: 57.7%         |
| <b>Flash Point</b>                       | 48°F   |
| <b>CPSC Flammability Classification</b>  | Flammable  |
| <b>Boiling Range</b>                     | 174°F to 375°F   |
| <b>VOC Category (Max Allowable VOC)</b>  | Adhesion Promoter (540 gm/liter)                           |
| <b>Actual VOC</b>                        | 540 gm/liter 4.5 lbs/gal 22.7%                             |
| <b>MAX Vapor Pressure of the V.O.C.:</b> | 11.4 mmHg @ 20°C   |
| <b>Storage</b>                           | Store between 32°F and 95°F, in the original container.    |
| <b>Density</b>                           | 0.9 gm/liter 7.9 lb/gal                                    |
| <b>Shelf Life</b>                        | 2 years from date of manufacture, in an unopened container |
| <b>DOT</b>                               | UN1263, Paint Related Material, 3, PGII, Ltd. Qty          |
| <b>HAPS</b>                              | Toluene, Xylene, Styrene, Ethyl Benzene                    |
| <b>Coverage</b>                          | 250 – 425 sq. ft. per quart                                |

### ORDERING INFORMATION

| Product | Size | Pack | Lbs | Case Cube | Unit Width | Unit Depth | Unit Height | UPC Code        | Pallet Qty |
|---------|------|------|-----|-----------|------------|------------|-------------|-----------------|------------|
| QTPO125 | QT   | 6    | 13  | .406      | 3.44"      | 3.44"      | 8.72"       | 0 30192 12515 1 | 528        |
| GTP0125 | GL   | 4    | 35  | .762      | 4.13"      | 6.63"      | 10.31"      | 0 30192 12525 0 | 208        |



©2009 W.M. Barr & Co., Inc.  
P.O. Box 1879  
Memphis, TN 38101  
800.238.2672  
www.bulldogsticks.com  
www.kleanstripauto.com

